




Fabrication of 3-D, Wavelength-Tuneable, Photonic Crystals for Space-based, mm-Wave, Terahertz, and Infrared Communications

Introduction

At the intersection of electronics and photonics, this collaborative research initiative with SmartSat CRC and La Trobe University emerges to advance tunable **Photonic Crystals** with the aim of enhancing **satellite-to-satellite** communication systems, **high-altitude balloon-to-balloon** or **satellite-to-high-altitude-balloon** connections.

Photonic crystals, periodic structures, enable intricate control of electromagnetic waves beyond traditional refraction or reflection. Our research centres on 3-D photonic crystals, offering superior band gaps and tunability. These crystals promise innovation in **advanced communication, sensing, and image filtering devices**. We are creating woodpile structures that act as 3D tunable Photonic Crystals.



Aims

Develop novel tunable photonic crystals at high pressures using HP-LCVD:

- Growth of **Carbon, Vanadia** and **Titania** fibres via HP-LCVD.
- Parallel growth of precision tapered and graded fibres.
- Creation of woodpile structure, graded materials, tapered materials, etc. for tunable Terahertz filters.

Methods

We're developing a novel fabrication technique, **Hyperbaric Pressure Laser Chemical Vapor Deposition (HP-LCVD)**, to grow 3-D microstructures. This method is perfect for crafting high precision metamaterials and photonic crystals. HP-LCVD employs a focused **laser beam** within a **hyperbaric chamber** to decompose precursor gases, allowing precise customization of 3-D microstructures through pressure, composition, and flow rate adjustments, creating versatile multi-material arrays.


References

- Lipson, R. H., and C. Lu. "Photonic crystals: a unique partnership between light and matter." *European Journal of Physics* 30.4 (2009): S33.
- Maxwell, J. L., et al. "High Temperature Nanocomposites For Nuclear Thermal Propulsion and In-Space Fabrication by Hyperbaric Pressure Laser Chemical Vapor Deposition." *Journal of the British Interplanetary Society* 66 (2013): 328-333.


HP-LCVD System Assembly




Eldex 5935 2SMP High-Pressure Liquid Metering Pump Setup



Parr Instrument NCC-4793HP-T-INC-5000-VGR-VDWINDOW(3)



Ytterbium CW Laser YLR-20-1064



Pyrometer Setup


Spectrometer

Optical Setup


Power meter

Results to date


We have successfully grown **carbon fibres** on both **graphite** and **stainless-steel** substrates, employing a variable laser power within the range of **100 mW to 3W** and operating at pressures ranging from **1 to 27 bar**. Our ongoing work involves the simultaneous parallel growth of multiple fibres, a significant advancement in our research.



(a) Terahertz Photonic Crystal Filter Woodpile structure



(b)




(c)

(b) Carbon Fibre grown on Stainless steel Substrate

(c) Twin crystal-like Carbon Fibre Growth



(d)



(e)

(d) Carbon Fibres Array on Graphite Substrate

(e) Multiple Laser Spot Setup for Parallel Fibre Growth